



Selectarc 20/10BC

*Stainless Steel
Rutile Electrode*

Classification

AWS A5.4 : E308L-16
ISO 3581-A : E 19 9 L R 3 2

EN 1600 : E 19 9 L R 3 2

Description & Applications

Low carbon Rutile-basic-coated austenitic stainless steel electrode with approx. 8% ferrite. Coating with very low moisture pick up. Soft fusion without spatters, very easy slag removal, exceptional weld bead appearance, easy restriking. Applied for all 18/8 type stainless steels at service temperatures from - 120°C up to +350°C.

Main applications: Tubes, tanks, heat exchangers, piping systems.

Base materials

Stainless steels for general use:

UNS	Alloy	EN 10088	Material N°	UGINE
S30400	304	X5CrNi18-10	1.4301	UGINOX 18-9 B, D, E
S30403	304L	X2CrNi19-11	1.4306	UGINOX 18-10 L
S32100	321	X6CrNiTi18-10	1.4541	UGINOX 18-10 T
S34700	347	X6CrNiNb18-10	1.4550	

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Fe
<0.03	0.8	0.7	19.0	9.5	Rem.

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>360	>540	>35	+20°C >70

Welding Current & Instructions

Electrode	ØxL (mm)	2,0x300	2,5x350	3,2x350	4,0x350	5.0x450
Current	(A)	45	70	100	135	180

Redrying at 250°C during 1h, if necessary. Interpass temperature: < 150°C.

ind.12



= +	~ 70V
-----	-------

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.