



Selectarc 24/12S

*Rutile type Stainless
Steel Electrode*

Classification

AWS A5.4 : E309L-16
ISO 3581-A : E 23 12 L R 3 2

EN 1600 : E 23 12 L R 3 2

Description & Applications

Low carbon Rutile-basic electrode with an austenitic stainless steel deposit containing 15% ferrite for welding dissimilar steels as stainless steels to low alloyed steels. Also suitable for welding high temperature steels and as buffer layer before hardfacing. For repairing of machine parts for civil engineering. First layer on construction steels for 18/8 cladding. Soft fusion, nice aspect of the bead, self releasing slag.

Base materials

Stainless steels for general use and for high temperature applications:

UNS	Alloy	EN	Material N°	UGINE
S30900	309	X15CrNiSi 20-12	1.4828	UGINOX R20-12
S30453	304 LN	X2CrNiN 18-10	1.4311	
S30908	309S	X12CrNi23-13	1.4833	UGINOX R24-13S
		X10CrSi6	1.4712	
		X10CrAl 18	1.4742	

All construction steels, low alloyed in combinations with stainless steels.

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Fe
<0.03	0.8	0.7	22.5	12.5	Rem.

All Weld Metal Mechanical Properties

R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>400	>560	>35	+20°C >60

Welding Current & Instructions

Electrode	ØxL (mm)	2,0x300	2,5x300	3,2x350	4,0x350	5,0x450
Current	(A)	45	70	100	135	180

Redrying at 250°C during 1 hour, if necessary. Interpass temperature : < 150°C.

ind.12



= + ~ 70V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.