



Selectarc 55

*Rutile Electrode
With a very thick coating*

Classification

AWS A5.1 : E6013

EN 499 : E 42 0 RR 1 2

ISO 2560-A : E 42 0 RR 1 2

Description & Applications

Thick coated rutile electrode destined for flat or for fillet welding when a nice aspect of the weld bead is searched. Concave bead on fillet welds, very soft fusion and a self releasing slag ; supports high current. Frequently used for final passes.

Base materials

Construction steels for general use , Tube steels, Ship steels

EN- Designation	S185 – S355 P235 – P355	L210 – L360
Ship steels	Quality A and B	
ASTM	A285 grade C A442 grade 55, 60	A414 grade C, D, E, F A515 grade 55, 60, 65

Typical Weld Metal Composition (%)


C	Si	Mn	P	S	Fe
<0.10	0.45	0.6	<0.025	<0.025	Rem.

All Weld Metal Mechanical Properties

R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>400	510-580	>22	+20°C >64 0°C >47 -20°C >28

Welding Current & Instructions

Electrode	ØxL (mm)	2,0x300	2,5x350	3,2x350	3,2x450	4,0x450	5,0x450
Current	(A)	70	90	135	135	180	250



= - ~ 45V

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.