



Selectarc B7016Sp

Basic Electrode

Double coated

Classification

AWS A5.1 : E7016

EN 499 : E 38 3 B 1 2 H10

ISO 2560-A : E 38 3 B 1 2 H10

Description & Applications

Basic coated electrode presenting exceptional welding characteristics due to its double coating. Arc very stable in all positions, almost spatter free, easy removal of the slag. Universal use for welding metal constructions and for repairing. Recommended for root passes and on badly prepared joints too.

Base materials

Construction steels for general use, Tube steels, Ship steels, Steels for Boiler and Pressure Vessels, High strength steels, Heat resisting steels, Cold tough steels

EN-Designation	S185 – S355 GP240R L210 – L360	P235 – P355 P235GH – P265GH
Ship steels	Quality A, B, C and D	
ASTM	A285 grade C A442 grade 55 , 60 A516 grade 55 , 60 , 65 ,70	A414 grade C, D, E, F A515 grade 55 , 60 , 65 , 70

Typical Weld Metal Composition (%)

C	Si	Mn	P	S	Fe
<0.10	0.7	0.9	<0.02	<0.02	Rem.

All Weld Metal Mechanical Properties

R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
450	550	27	+20°C	150
			-20°C	80
			-50°C	70

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	3,2x450	4,0x450	5,0x450
Current	(A)	80	115	115	150	190

Redrying: 2h at 300°C, if necessary. Interpass temperature: < 250°C.

Ind.12



= + ~ 70V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.