



Selectarc B72

*High Strength
Basic Electrode*

Classification

AWS A5.5 : E9018-G

ISO 18275-A : E 55 5 1NiMo B 4 2 H5

Description & Applications

Low hydrogen basic coated electrode with a deposit which has a high yield strength and is very tough. Particularly recommended for root passes on fine grain steels resistant to a tensile strength between 550 and 700 MPa (ex : rails of travelling crane...).

Base materials

Construction steels for general use:

DIN 17100 : St50 - St52 - St60-2.

High strength steels :

NF A 36-207 : A550AP, FP – A590AP,FP

NF A 36-210 : 16MND5

ASTM A202 Gr A & B – A236 F & B – A238GrB – A486Gr90

A607Gr70 – A615Gr60 – A706 Gr60.

DIN : StE355 to WStE500

17MnMoV6.4 – 15NiCrMo10.6

N-AXTRA55, N-AXTRA60 (Thyssen)

API : X65 - X70

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Mo	Fe
<0.10	0.5	1.2	0.1	0.8	0.3	Rem.

All Weld Metal Mechanical Properties


R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
>530	>620	>20	+20°C	>150
			-50°C	>50
			-60°C	>28

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450	5,0x450
Current	(A)	80	115	150	190

Redrying at 350°C during 2 hours. Eventual preheating depends on the nature and the thickness of the steel (100°C). Interpass temperature <200°C. A thermal stress relieving is advised in most cases at 600°C during 2 hours

ind.12



= +

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.