



Selectarc B84

*Basic Electrode
With high toughness*

Classification

AWS A5.5 : E8018-C2 EN 499 : E 46 6 3Ni B 4 2 H5
ISO 2560-A : E 46 6 3Ni B 4 2 H5

Description & Applications

Low hydrogen basic coated electrode alloyed with Nickel (above 3%) for welding fine grain steels used at low temperature (-60 to -80°C).

Main applications: Cryogenic and petrochemical industries. Storage and distribution of liquid gas or products volatile.

Base materials

Plates and tubes of fine grain steels, cold tough:

NF A 35-207	:	A510FP1 – A550FP2
NF A 36-208	:	3.5 Ni 285 and 355 (12N14)
DIN	:	10Ni14 – 14Ni6 – 16Ni14
ASTM	:	A203G D&E – A352GrLC3 – A334Gr3 – A350Gr LF3

Typical Weld Metal Composition (%)

C	Si	Mn	Ni	P	S	Fe
<0.10	0.3	0.9	3.5	<0.025	<0.025	Rem.

All Weld Metal Mechanical Properties

R _e (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>460	>550	>19	-73°C >80 -100°C >30

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450	5,0x450
Current	(A)	80	115	150	190

Redrying at 350°C during 2 hours, if necessary. An eventual preheating depends on the thickness of the parent metal. A stress relieving heat treatment is recommended in most of cases (620°C/1h).

ind.12



= +

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr