



Selectarc Co12

*"Grade 12" type cobalt base
Hardfacing Electrode*

Description & Applications

Hardfacing electrode with a rutile-basic coating. Cobalt base deposit of « stellite grade 12 » type (Co-Cr-W). The deposit with a high hardness is characterised by a very good resistance to metal and mineral abrasion combined with corrosion and high temperature up to 800°C, in the presence of moderate shocks. Highly resistant to erosion and cavitation. Highly recommended when an important hardness is searched and for a deposit stressed by temperature, corrosion, abrasion and impact. Excellent welding characteristics.

General application: Hardfacing of tools for processing plastics, for wood and paper (carton and paper cutting) characteristics, pressing tools, hot cut tools , hot shear blades, extrusion screws, ...

* Note : "Stellite" is a trade mark of Deloro Stellite (Haynes International).

All Weld Metal Mechanical Properties

Hardness (as welded) +20°C
~ 50 HRC

Hardness (as welded) +600°C
38-40 HRC

Welding Current & Instructions

Electrode	ØxL (mm)	3,2x350	4,0x350	5,0x450
Current	(A)	100	140	180

Redrying 1h at 250°C, if necessary. Preheat massive pieces 250-400°C. Use a low current in order to limit the dilution with the base metal and to conserve the hardness of this alloy. Cool down slowly in order to limit the risk of cracks in the deposit. Weld eventual cushion layers with Selectarc 307R.

ind.13



= + ~ 70V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr