



Selectarc Cu115

Copper Tin Electrode
For DC

Classification

AWS A5.6 : ECuSn-C DIN 1733 : EL-CuSn7
ISO 17777 : E Cu 5180B (CuSn7) N° de Mat. : 2.1025

Description & Applications

Basic coated electrode for welding copper tin bronzes (Cu-Sn 6-8%) and bronzes (Cu-Zn) in some cases too. Also used for dissimilar joints. Selectarc Cu115 is recommended for repairing wrought bronzes (Cu-Sn), for surfacing on bronzes, steels and cast iron. The deposit is resistant to salt water corrosion.

Main applications: Construction of equipment for the chemical industry and petrochemical industry, naval constructions and installations for sea water desalination, repair works.

Base materials

UNS	DIN	Material N°
C50700	CuSn2	2.1010
C51100	CuSn4	2.1016
C51900	CuSn6	2.1020
C52100	CuSn8	2.1030
	CuSn6Zn	2.1080
C52400	G-CuSn10	2.1050

Typical Weld Metal Composition (%)

Sn	Mn	Fe	P	Cu
7.0	0.9	0.15	0.1	Rem.

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
120	300	>20	110 HB

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x350
Current	(A)	70-90	90-110	110-130

Redrying 2 h at 150°C. Joints to weld must be clean, exempt from grease, cracks. Guide electrodes with a slight declination (10-20°) inclined in direction of travel). Weld with a short arc. To improve degassing of the deposit, adopt a low welding speed. Heavy pieces (sections above 6 mm) have to be preheated to 150-300°C.

Ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.