



Selectarc HB56HT

Basic coated Electrode

For hot working tools

Description & Applications

The weld deposit distinguishes itself by its high hardness, toughness and heat resistance. Therefore the electrode is used for overlay and builds up of machinery parts and tools subject to impact, compression and wear used at operating temperatures up to 550°C .

General applications: For building up hammers, dies, swages, hot shear blades, rollers, extrusion press pistons, valves, etc...

Base materials High strength carbon steels and hot working steels

Material N°	DIN classification	Material N°	DIN classification
1.2311	40CrMnMo 7	1.2367	X38CrMoV 5 3
1.2343	X38CrMoV 5 1	1.2606	X37CrMoW 5 1
1.2344	X40CrMoV 5 1	1.2713	55NiCrMoV 6
1.2365	X32CrMoV 3 3	1.2714	56NiCrMoV 7

All Weld Metal Mechanical Properties

Hardness (as welded)


53-58 HRC

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x450
Current	(A)	60-90	80-110	100-140

Preheat the workpiece to 250-400°C depending on thickness and alloy. Hold the electrode vertically with a short arc. Keep temperature during welding and let the workpiece cool slowly. Subsequent machining is possible by grinding or with tungsten carbide tools.

ind.13



= +,- ~ 70V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr