



Selectarc HB61R

*Hardfacing Electrode resistant to
Impact, compression and abrasion*

Description & Applications

Rutile-basic coated general purpose hardfacing electrode for applications subject to impact, compression and abrasive wear. For hardfacing on components made of C-steel, cast steel and Manganese steel. The deposit is tough-hard and crack resistant. Recovery of the electrode approx. 120%.

General applications: Hardfacing of block presses, crusher jaws, wheel rims, rollers, caterpillar tracks, ploughshares, running surfaces, cutting edges etc...

All Weld Metal Mechanical Properties

Hardness

56-60 HRC

Obtained in pour weld metal

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450
Current	(A)	60-90	90-120	110-160

Redrying, if necessary, 2h/300°C. Guide electrode almost vertically with a short arc. On materials sensitive to cracks a buffer-layer with selectarc 18/8Mn is recommended. Low alloyed, high carbon tool steels etc. have to be preheated to 200-400°C, depending on their composition and thickness. Slow cooling in still air after surfacing.

ind.13



= + ~ 50V

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr