



Selectarc HBMnCr

Electrode highly Resistant to Cavitation

Description & Applications

Synthetic basic coated electrode with high efficiency (140%), intended to surface all pieces subject to high impact and cavitation combined with corrosion. Also used for dissimilar joints between Mn- and construction steels and as cushion layer before hardfacing in case of heavy reclaiming. The deposit is austenitic and is exceptionally resistant to impact and wear combined with impact. The high amount of Cr increases the resistance against corrosion, abrasion and cavitation.

General applications: Repairing of used pieces or preventive protection of new pieces used in railway applications (rails, switches, crossings, tongues) in quarries and mines (crusher jaws, excavator and grab teeth, mill hammers, rock crusher) for hydro power stations and other industries (pistons of hydraulic presses, turbines).

Base materials

Austenitic steels with high Mn:

DIN 17145 and 17155 : X110Mn14

AFNOR : Z120M12

All Weld Metal Mechanical Properties

Hardness as welded

~ 260 HB

Obtained in pour weld metal

Hardness after work hardening

400-500 HB

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x350	3,2x350	4,0x450	5,0x450
Current	(A)	90	130	160	220

Redrying 1h at 300°C, if necessary. Weld with a minimum heat input (low current, short beads) in order to respect an interpass temperature of 250°C maximum. Do not preheat the piece to weld!

Ind.13



= +

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr