



Selectarc Inox 308B

*Basic coated
Stainless Steel Electrode*

Classification

AWS A5.4 : E308L-15
ISO 3581-A : E 19 9 L B 4 2

EN 1600 : E 19 9 L B 4 2

Description & Applications

Low carbon austenitic stainless steel electrode, basic type coating with ~ 8% ferrite. Stable arc, good slag removal, regular weld beads. Good behaviour in positional welding and on bad prepared joints. Excellent mechanical properties. Used on 18/8 stainless steels for service temperatures from -196 °C up to +350 °C.

Main applications: For tubes, tanks, heat exchangers, piping systems.

Base materials

Stainless steels for general use:

UNS	Alloy	EN 10088	Material N°	UGINE
S30400	304	X5CrNi18-10	1.4301	UGINOX 18-9 B, D, E
S30403	304L	X2CrNi19-11	1.4306	UGINOX 18-10 L
S32100	321	X6CrNiTi18-10	1.4541	UGINOX 18-10 T
S34700	347	X6CrNiNb18-10	1.4550	

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Ni	Fe
<0.04	0.4	1.6	19.0	9.5	Rem.

All Weld Metal Mechanical Properties



R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>380	>560	>35	+20°C >90 -196°C >30

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350
Current	(A)	70	90	120

Redrying at 250°C during 1 hour, if necessary. Inte rpass temperature : < 150°C.

ind.12



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.