

## Selectarc Inox 310H

High Temperature Stainless Steel Electrode

## Classification

AWS A5.4 : E310H-15 EN 1600 : E 25 20 H B 4 2

ISO 3581-A : E 25 20 H B 4 2

**Welding Current & Instructions** 

## **Description & Applications**

Basic coated austenitic stainless steel electrode with 26%Cr, 21%Ni and an increased carbon contend. Used to weld austenitic heat resistant alloys, centrifugally cast tubes etc. resisting to scaling and oxidation up to 1100°C. Regular and stable fusion, good slag removal, nice aspect of the bead.

Main applications: Petrochemical industry, for furnaces, reformer and steam cracker tubes, piping systems.

**Base materials** 

UNS	Alloy	EN	Material N°
J93503		G-X40CrNiSi25-12	1.4837
J94204	HK 40	G-X40CrNiSi25-20	1.4848

Typical Weld Metal Composition (%)						
С	Si	Mn	Cr	Ni	Мо	Fe
0.4	0.7	2.0	26.0	21.0	0.2	Rem.

All Weld Metal Mechanical Properties					
R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )			
>450	>650	>15			

Electrode	ØxL ( mm )	2,5x300	3,2x350	4,0x350
Current	( A )	70	100	135

Redrying 2 hours at 250 $^{\circ}$ C, if necessary. Interpass temperature : < 150 $^{\circ}$ C.





ind.12

