

# Selectarc Inox 316L

Stainless Steel Rutile Electrode

## Classification

AWS A5.4 : E316L-17 EN 1600 : E 19 12 3 L R 3 2

ISO 3581-A : E 19 12 3 L R 3 2

## **Description & Applications**

Low carbon Rutile-basic-coated Mo containing austenitic stainless steel electrode with approx. 8% ferrite. Coating with very low moisture pick-up. Soft fusion without spatters, very easy slag removal, exceptional bead appearance, easy restriking. Exceptional welding in position. For welding and cladding on austenitic Cr-Ni-Mo stainless steels and clad plates. Applied for service temperatures from -120°C up to +400°C in the chemical and petrochemical industries, in refineries, in the food industries and for ship building to weld pipes, tanks, heat exchangers.....

#### **Base materials**

Stainless steels for general use:

Starines.	3 316613 1	oi general use.		
UNS	Alloy	EN 10088	Material N°	UGINE
S3 <mark>1</mark> 600	316	X5CrNiMo17-22-2	1.4401	UGINOX 17-10 M
S31603	316L	X2CrNiMo17-12-2	1.4404	UGINOX 18-11 ML
J92900		G-X5CrNiMo 19 11 2	1.4408	
S31635 316Ti		X6CrNiMoTi17-12-2	1.4571	UGINOX 17-11 MT
S31635	316Ti	X10CrNiMoTi18-12	1.4573	
S31640	316Cb	X6NiCrMoNb17-12-2	1.4580	
		G-X5CrNiMoNb19-11-2	1.4581	

## Typical Weld Metal Composition (%)

С	Si	Mn	Cr	Ni	Мо	Fe
< 0.03	0.8	0.7	18.5	12.2	2.8	Rem.

#### **All Weld Metal Mechanical Properties**

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV (J)
450	580	40	+20°C 70
			-120°C 40

## **Welding Current & Instructions**

Electrode	ØxL ( mm )	2,0x300	2,5x350	3,2x350	4,0x450	5,0x450
Current	(A)	45	75	110	140	180

Redrying at 250°C during 1h, if necessary. Interpass temperature : < 150°C.



= + ~ 70V



