



# Selectarc Inox 317L

*Stainless steel Electrode*

*With 3.5% Mo*

## Classification

AWS A5.4 : E 317L-17

EN 1600 : E Z 19 13 4 L R 3 2

ISO 3581-A : E Z 19 13 4 L R 3 2

## Description & Applications

Low carbon Rutile-coated austenitic stainless steel electrode with ~3,5% of Molybdenum and approx. 8% ferrite. The electrode has a coating with very low moisture pick up. Soft fusion, without spatters, very easy slag removal, exceptional weld bead appearance, easy re-striking. Designed for welding and hardfacing stainless steels like 316L and 317L as well as stabilised grades. Pitting corrosion increased with regard Inox 316L.

### Base materials:

### Stainless steels for general use :

UNS	Steels	EN 10088	Alloy N°	UGINE
S31603	316L	X2CrNiMo17-12-2	1.4404	UGINOX 18-11ML
S31653	316LN	X2CrNiMoN17-13-3	1.4429	UGINOX 17-10 M
S31700	317	X5CrNiMo17-13-3	1.4449	
S31703	316LMo	X2CrNiMo18-14-3	1.4435	UGINOX 18-13MS
S31703	317L	X2CrNiMo18-15-4	1.4438	

## Typical Weld Metal Composition ( % )

C	Si	Mn	Cr	Ni	Mo	Fe
0.02	0.8	0.7	19.0	13.0	3.5	Rem.

## All Weld Metal Mechanical Properties

R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
470	600	35	+20°C 60

## Welding Current & Instructions

Electrode	ØxL ( mm )	2,0x300	2,5x300	3,2x350	4,0x350
Current	( A )	45	75	110	140

Redrying 1h at 250°C, if necessary. Interpass temperature: <200°C.

Ind.12



= + ~ 70V



**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.