



Selectarc Ni625BF

*Nickel base Electrode
highly corrosion resistant*

Classification

AWS A5.11 : ENiCrMo-3
UNS : W86112

ISO 14172 : E-Ni 6625 (NiCr22Mo9Nb)

Description & Applications

Basic coated electrode with an alloyed core wire for welding of Nickel-Chromium-Molybdenum alloys to themselves and to lower alloyed steels as well as for welding of special austenitic stainless steels. Good weldability in all positions, except vertical down; stable arc, medium slag removal, regular weld beads. Due to its composition the weld metal is highly resistant to corrosion and presents a high yield and a high tensile strength.

Main applications: Welding of Off-shore components, boilers, vessels, piping systems in the chemical and petrochemical industries as well as components of flue gas desulfurizing plants.

Base materials:

UNS	Alloy	DIN	Material N°
K81340	9%Ni	X8Ni9	1.5662
N06625	625	NiCr22Mo9Nb	2.4856
N08825	825	NiCr21Mo	2.4858
N08904	904L	X1NiCrMoCuN25 20 5	1.4539
N08926	254SMo	X1NiCrMoCuN25 20 6	1.4529

Typical Weld Metal Composition (%)

C	Si	Mn	Cr	Mo	Nb+Ta	Fe	P	S	Cu	Ni
<0.03	0.4	<0.1	22.0	9.0	3.6	0.6	<0.020	<0.010	<0.1	base

All Weld Metal Mechanical Properties


R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
>480	>780	>30	+20°C >80

Welding Current & Instructions

Electrode	ØxL (mm)	2,5x300	3,2x350	4,0x350	5,0x450
Current	(A)	50-70	70-100	90-120	140-160

Redrying 1h at 250-300°C. Joints to weld must be clean, exempt from grease, cracks. Guide electrodes with a slight declination, weld with a short arc and prevent a high heat input by applying the stringer bead technique (weaving max. 2 times core wire diameter). Nickel base alloys are welded without preheating and an interpass temperature <150°C.

FT En-466-171011



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.