



FCO 66

*Self-shielded hardfacing wire
for severe abrasion*

Classification

EN 14700 : T Fe16

Description & Applications

Tubular flux cored wire for self-shielded metal arc hardfacing of components subjected to several abrasions with or without shocks, at service temperature up to 600°C. Hardfacing possible in 2 or 3 layers max. Relief checking is normal.

Main applications: Ash plows, coke crusher segments, screw conveyers, valves, exhaust fans, rake teeth in furnaces ...

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Mo	W	V	Nb	P	S	Fe
Min	4			10							
Max	8		3	40	10	10	10	10			Rem.
Type	5.5	1.5	0.50	22.0	5.5	2.0	1.0	6.0	0.015	0.010	Rem.


All Weld Metal Mechanical Properties

Hardness (3rd layer)

64 - 66 HRC as welded

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick out (mm)	
FCAW = +	1.6	150 - 350	26 - 30	25 - 30	-
	2.4	250 - 450	26 - 32	25 - 40	



FT En-CM21-180924

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr