



FCW 308LP

*All position 308L type
Flux cored wire*

Classification

AWS A5.22 : E308LT1-1/-4

ISO 17633-A : T 19 9 L P M21(C1) 1

Description & Applications

Flux cored wire for gas shielded (Ar + CO₂) arc welding for 304L stainless steel. Wire with rutile fast freezing to weld easily in all positions. For all type of steel construction with a service temperature does not exceed 400°C.

Main applications: Thermal Plant, piping, construction on sea coast

Base materials:

UNS	Grade	EN 10088	N° Mat.
S30400	304	X5CrNi18-10	1.4301
S30403	304L	X2CrNi19-11	1.4306
S32100	321	X6CrNiTi18-10	1.4541
S34700	347	X6CrNiNb18-10	1.4550

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	P	S
Min			0.5	18.0	9.0				
Max	0.04	1.0	2.0	21.0	11.0	0.30	0.5	0.030	0.025
Type	0.03	0.70	1.4	20.0	10.5	0.10	0.10	0.020	0.008

FN 8 (Feritscope)


All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	320	520	30	
Max				
Type	460	620	40	+20°C : 60 -196°C : 35

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick out (mm)	
FCAW = +	1.2	130 - 270	22 - 35	12 - 25	ISO 14175 : M21 (Ar/CO ₂) 10 - 20 l/min

FT En-CN06-190731



Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr