



# FCW 309LP

*All position 309L type  
Flux cored wire*

## Classification

AWS A5.22 : E309LT1-1/-4

ISO 17633-A : T 23 12 L P M21(C1) 1

## Description & Applications

Flux cored wire for gas shielded (Ar + CO<sub>2</sub>) arc welding for 309L stainless steel and for dissimilar joining type 304 or 316 on low alloys steels. The high ferrite content allows an important dilution without cracks. Wire with rutile fast freezing to weld in all positions.

**Main applications:** Pressure vessels, maintenance and repair. Buttering before Low carbon cladding or Final hardfacing

## Typical Chemical Composition ( % )

	C	Si	Mn	Cr	Ni	Mo	Cu	P	S
Min			0.5	22.0	12.0				
Max	0.04	1.0	2.5	25.0	14.0	0.3	0.5	0.030	0.025
Type	0.03	0.80	1.4	23.5	12.5	0.08	0.08	0.020	0.008


FN 23 (Feritscope)

## All Weld Metal Mechanical Properties

	R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
Min	320	520	30	
Max				
Type	460	580	35	-60°C 45

## Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters			Shielding Gas
		Current (A)	Voltage (V)	Stick out (mm)	
FCAW = +	1.2	130 - 270	22 - 35	12 - 25	ISO 14175 : M21 (Ar/CO <sub>2</sub> ) 10 - 20 l/min



FT En-CN10-190731

**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

[www.fsh-welding.com](http://www.fsh-welding.com) - [info@fsh-welding.fr](mailto:info@fsh-welding.fr)