



MIG 20/10MNB

Classification

AWS A5.9 : ER318

ISO 14343-A : G 19 12 3 Nb

Description & Applications

Low carbon solid wire for GMAW of stainless steels stabilised with Niobium like 318 or with Titanium like 316Ti. Good resistance against intergranular corrosion, device corrosion in chloride atmosphere with service temperature up to 400°C and oxydation.

Main applications: Petrochemical industries and for sea water applications.

Base materials:

Stainless steels for general use:

UNS	Alloy	EN 10088	Material N°
S31600	316	X5CrNiMo17-12-2	1.4401
S31603	316L	X2CrNiMo17-12-2	1.4404
S31635	316Ti	X6CrNiMoTi17-12-2	1.4571
S31640	316Cb	X6CrNiMoNb17-12-2	1.4404

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	Nb	P	S	Co	N
Min		0.30	1.0	18.0	11.0	2.5		10 x C			-	-
Max	0.08	0.65	2.5	20.0	14.0	3.0	0.5	1.0	0.03	0.02	-	-
Type	0.04	0.40	1.7	19.6	11.5	2.6	0.20	0.60	0.02	0.01	0.06	0.05

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	350	550	25	-
Max				-
Type	400	620	35	+20°C 120

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current (A)	Voltage (V)	
GMAW = +	0.8	70 - 180	18 - 26	ISO 14175: M12 (Ar+0.5-5%CO ₂) M13 (Ar+0.5-3%O ₂) 15-20 l/min
	1.0	80 - 220	18 - 28	
	1.2	150 - 320	22 - 32	
	1.6	220 - 380	24 - 34	

Back shielding with Argon or Nitrogen gas or with copper backing support to avoid "back end" rust phenomena.

FT En-MN15-19118

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr