



MIG 20/10NB

Classification

AWS A5.9 : ER347
AMS : 5680

ISO 14343-A : G 19 9 Nb
AIR 9117 : Z10 CNNb 18-11

Description & Applications

Solid wire for GMAW of stainless steels stabilised with Niobium like 347, with Titanium like 321 or low carbon content stainless steels like 304L and controlled Carbon content like 304H. Good intergranular resistant corrosion.

Main applications: Aeronautical industry, petrochemistry, power plant.

Base materials:

Stainless steels for general use and for high temperature applications:

UNS	Alloy	EN 10088	Material N°
S30409	304H	X6CrNi18-11	1.4948
S30400	304	X5CrNi18-10	1.4301
S32100	321	X6CrNiTi18-10	1.4541
		X10CrNiTi18-10	1.6903
		X10CrNi18-8	1.4310
S30403	304L	X2CrNi19-11	1.4306

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	Nb	P	S	Co	N
Min		0.30	1.0	19.0	9.0			12 x C			-	-
Max	0.08	0.65	2.5	21.0	11.0	0.5	0.5	1.0	0.03	0.02	-	-
Type	0.045	0.40	1.5	19.4	9.3	0.10	0.10	0.60	0.02	0.01	0.06	0.06

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	350	550	30	-
Max				-
Type	490	660	35	+20°C 140

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current (A)	Voltage (V)	
GMAW = +	0.8	70 - 180	18 - 26	ISO 14175: M12 (Ar+0.5-5%CO ₂) M13 (Ar+0.5-3%O ₂) 15-20 l/min
	1.0	80 - 220	18 - 28	
	1.2	150 - 320	22 - 32	
	1.6	220 - 380	24 - 34	

Back shielding with Argon or Nitrogen gas or with copper backing support to avoid "back end" rust phenomena.

FT En-MN08-200325

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr