



MIG CUNI10

Old reference: MIG CuNi90.10

Classification

ISO 24373 : S Cu 7061 (CuNi10)

Description & Applications

Solid wire for GMAW of Copper-Nickel alloys types CuNi90/10.

Main applications: For offshore applications, seawater desalination plants, for ship building, in the chemical industry.

Base materials:

UNS	Alloy	DIN	Material N°
C70600	CuNi90/10	CuNi10Fe1Mn	2.0872

Typical Chemical Composition (%)

	Fe	Mn	Ni+Co	P	Pb	Si	C	Ti	S	O/T	Cu
Min	0.5	0.5	9.0					0.1			
Max	2.0	1.5	11.0	0.02	0.02	0.2	0.05	0.5	0.02	0.4	Rem.
Type	1.4	0.8	10.5	0.004	0.01	0.02	0.01	0.4	0.004	<0.4	Rem.

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)
Min	-	-	-
Max			
Type	200	320	15

Welding Current & Instructions

	Ø (mm)	Welding parameters		Shielding gas
		Current (A)	Voltage (V)	
GMAW = +	0.8	120 - 180	20 - 22	ISO 14175: I1 (100% Ar) I2 (100% He) I3 (Ar+ 5-30%He) 12-18 l/min
	1.0	180 - 220	22 - 24	
	1.2	220 - 250	24 - 26	

Preheating of massive parts between 200°C (>6mm) up to 500°C (>15mm).

FT En-MU12-200302

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group.

Fumes: Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr