

MIG D25/09W

Classification

AWS A5.9 : ER2594 ISO 14343-A : G 25 9 4 N L

Description & Applications

Low carbon content solid wire for GMAW of Duplex and Super Duplex (austenitic-ferritic microstructure) type stainless steels. Resistant in chloride containing media against pitting corrosion as well as crevice and stress corrosion. Used for components which require high strength combined with corrosion attack. Could be used with service temperature up to +250°C.

Main applications: For pumps, vessels, piping systems

Base materials

Austenitic-ferritic stainless steels

UNS	Alloy	EN 10088	Material N°
S31803		X2CrNiMoN22-5-3	1.4462
S32304	35N	X2CrNi23-4	1.4362
S32900	329	X3CrNiMoN27-5-2	1.4460
S32550	52N	G-X2CrNiMoCuN26-6-3	1.4517
	52N+	X2CrNiMoCuN25-6-3	1.4507
S32750	2507	X2CrNiMoN25-7-4	1.4410
S32760	100	X2CrNiMoCuWN25-7-4	1.4501

Typical Chemical Composition (%)

	С	Si	Mn	Cr	Ni	Mo	Cu	Nb	Р	S	Co	W	Ν	Pren
Min				24.0	8.0	2.5		-			-		0.20	-
Max	0.03	1.0	2.5	27.0	10.5	4.5	1.5	-	0.03	0.02	-	1.0	0.30	-
Туре	0.018	0.30	0.80	25.2	9.3	3.7	0.60	0.01	0.02	0.01	0.05	0.70	0.25	>40.0

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	550	760	18	-	-
Max				-	-
Туре	730	900	25	+20°C -40°C	150 120

Welding Current & Instructions

Wolding mode	Wire Ø	Welding p	Shiolding Goo	
Welding mode	(mm)	Current (A)	Voltage (V)	Shielding Gas
GMAW = +	0.8 1.0 1.2 1.6	70 - 180 80 - 220 150 - 320 220 - 380	18 - 26 18 - 28 22 - 32 24 - 34	ISO 14175: M12 (Ar+0.5-5%CO ₂) M13 (Ar+0.5-3%O ₂) 15-20 I/min

Back shielding with Argon or Nitrogen gas or with copper backing support to avoid "back end" rust phenomena.

FT En-MN33-191118