



MIG NI625

Classification

AWS A5.14 : ERNiCrMo-3 ISO 18274 : S Ni 6625 (NiCr22Mo9Nb)
AMS : 5837

Description & Applications

Solid wire for GMAW of high nickel alloys like Inconel 625 as well as special austenitic stainless steels. Used in the construction of equipment submitted to oxidizing and corrosive attacks. Excellent resistance to pitting, crevice and stress corrosion cracking in the presence of chlorides. Highly resistant at low temperatures, therefore also applied to weld 9% Ni steels. Could be used for heterogenous assembly between C-Mn or low alloy steels and stainless steels or nickel alloys.

Main applications: Cryogenic applications, chemical and petrochemical industries, aeronautic industry.

Base materials :

UNS	Alloy	DIN	Material N°
K81340	9%Ni	X8Ni9	1.5662
N06625	625	NiCr22Mo9Nb	2.4856
N08825	825	NiCr21Mo	2.4858
N08904	904L	X1NiCrMoCuN25-20-5	1.4539
N08926	254SMo	X1NiCrMoCuN25-20-6	1.4529

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Mo	Cu	P
Min				20.00	8.00		
Max	0.10	0.50	0.50	23.00	10.00	0.50	0.015
Type	0.01	0.15	0.10	22.0	8.7	0.01	0.007
	S	Fe	Nb+Ta	Co	Al	Ti	Ni
Min			3.20				58.0
Max	0.015	5.00	4.10	1.00	0.40	0.40	
Type	0.003	0.30	3.6	0.01	0.10	0.20	>58.0

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)	
Min	-	-	-	-	-
Max					
Type	520	790	40	+20°C	160
				-196°C	100

Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current (A)	Voltage (V)	
GMAW = +	0.8	70 - 180	18 - 26	ISO 14175: I1 (100% Ar) I3 (Ar+10-30%He) Z (Ar+He+H+CO ₂) 15-20 l/min
	1.0	80 - 220	18 - 28	
	1.2	150 - 320	22 - 32	
	1.6	220 - 380	24 - 34	

FT En-MI12-200901

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr