



TIG 20/10MN

Old reference: TIG 316LMn

Classification

AWS A5.9 : ER316LMn

ISO 14343-A : W 20 16 3 Mn N L

Description & Applications

Low Carbon solid rod for GTAW of austenitic stainless steels like 316L or 304L grade used for cryogenic applications. Non-magnetic and free of ferrite on weld deposit.

Main applications: Cryogenic applications.

Base materials:

Stainless steels for cryogenic applications:

UNS	Alloy	EN 10088	Material N°
S31603	316L	X2CrNiMo17-12-2	1.4404
S30403	304L	X2CrNi18-10	1.4306

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	Nb	P	S	Co	N
Min		0.30	5.0	19.0	15.0	2.5		-			-	0.10
Max	0.03	0.65	9.0	22.0	18.0	3.5	0.5	-	0.03	0.02	-	0.20
Type	0.02	0.50	7.0	20.0	16.0	3.0	0.15	0.01	0.02	0.01	0.06	0.15

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	350	550	25	-
Max				-
Type	500	650	30	+20°C : 140 -196°C : 95

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175 : I1 (Ar) 6-12 l/min Back shielding: I1 (Ar) / N1 (Nitrogen) : 3-6 l/min

Back shielding with Argon or Nitrogen gas or with copper backing support to avoid "back end" rust phenomena.

FT En-TN14-200406