



# TIG 20/10MNB

Old reference: TIG 318

## Classification

AWS A5.9 : ER318

ISO 14343-A : W 19 12 3 Nb

## Description & Applications

Low carbon solid rod for GTAW of stainless steels stabilised with Niobium like 318 or with Titanium like 316Ti. Good resistance against intergranular corrosion, device corrosion in chloride atmosphere with service temperature up to 400°C and oxydation.

**Main applications:** Petrochemical industries and for sea water applications.

**Base materials:**

**Stainless steels for general use:**

UNS	Alloy	EN 10088	Material N°
S31600	316	X5CrNiMo17-12-2	1.4401
S31603	316L	X2CrNiMo17-12-2	1.4404
S31635	316Ti	X6CrNiMoTi17-12-2	1.4571
S31640	316Cb	X6CrNiMoNb17-12-2	1.4404

## Typical Chemical Composition ( % )

	C	Si	Mn	Cr	Ni	Mo	Cu	Nb	P	S	Co	N
Min		0.30	1.0	18.0	11.0	2.5		10 x C			-	-
Max	0.08	0.65	2.5	20.0	14.0	3.0	0.5	1.0	0.03	0.02	-	-
Type	0.04	0.40	1.7	19.6	11.5	2.6	0.20	0.60	0.02	0.01	0.06	0.05

## All Weld Metal Mechanical Properties

	R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
Min	350	550	25	-
Max				-
Type	400	620	35	+20°C 120

## Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175 : I1 (Ar) 6-12 l/min Back shielding: I1 (Ar) / N1 (Nitrogen) : 3-6 l/min

Back shielding with Argon or Nitrogen gas or with copper backing support to avoid "back end" rust phenomena.

FT En-TN15-200406