



TIG 20/10NBS

Old reference: TIG 347Si

Classification

AWS A5.9 : ER347Si

ISO 14343-A : W 19 9 Nb Si

Description & Applications

Solid rod with Silicon increased content for GTAW of stainless steels stabilised with Niobium like 347, with Titanium like 321 or low carbon content stainless steels like 304L and controlled Carbon content like 304H. Good intergranular resistant corrosion.

High Silicon content improves alloy fluidity during welding.

Main applications: Aeronautical industry, petrochemistry, power plant.

Base materials:

Stainless steels for general use and for high temperature applications:

UNS	Alloy	EN 10088	Material N°
S30409	304H	X6CrNi18-11	1.4948
S30400	304	X5CrNi18-10	1.4301
S32100	321	X6CrNiTi18-10	1.4541
		X10CrNiTi18-10	1.6903
		X10CrNi18-8	1.4310
S30403	304L	X2CrNi19-11	1.4306

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	Nb	P	S	Co	N
Min		0.65	1.0	19.0	9.0			10 x C			-	-
Max	0.08	1.00	2.5	21.0	11.0	0.5	0.5	1.0	0.03	0.02	-	-
Type	0.04	0.80	1.5	19.5	9.8	0.20	0.10	0.60	0.02	0.01	0.06	0.06

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	350	550	25	-
Max				-
Type	460	630	33	+20°C : 110 -196°C : 30

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175 : I1 (Ar) 6-12 l/min Back shielding: I1 (Ar) / N1 (Nitrogen) : 3-6 l/min

Back shielding with Argon or Nitrogen gas or with copper backing support to avoid "back end" rust phenomena.

FT En-TN09-200406

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr