



TIG CO25

Classification

AMS : 5796

EN 14700 : S Z Co1

DIN 8555 : WSG 20-GZ-250-CKTZ

Description & Applications

Cobalt base solid rod for TIG or oxyfuel harfacing of Stellite™ Grade 25*. Good resistance to metal-metal wear and oxidation resistant up to 1000°C. Good behaviour to important thermal and mechanical shocks. Excellent resistance to cracks, work hardenable, highly resistant to cavitation and erosion. Deposit non-magnetic.

Main applications: Surfacing of motor valves, gas turbine blades, extrusion nozzles, forging dies, forging tools.

* Trademark Kennametal

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Fe	W	Nb	P	S	A/T	Co
Min	0.05		1.00	19.00	9.00			14.00					
Max	0.15	1.00	2.00	21.00	10.00		3.00	16.00		0.04	0.03	0.50	Rem.
Type	0.10	0.70	1.2	19.8	9.8	0.03	2.0	15.0	0.01	0.02	0.015	<0.50	Rem.

All Weld Metal Mechanical Properties

Hardness (as welded)

~230 HB

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175 : I1 (Ar) 6-12 L/min

Preheat large components or special steels to 200-400°C. Keep this temperature during welding and cool down slowly, preferable in an oven, to reduce the risk of cracking while cooling.

FT En-TB05-190514

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr