



TIG CUA9NI

Old reference: TIG CuAl9Ni

Classification

AWS A5.7 : ERCuNiAl

ISO 24373 : S Cu 6328 (CuAl9Ni5Fe3Mn2)

Description & Applications

Solid rod for GTAW of cupro-aluminium alloys with similar chemical composition. It has better resistance to wear and corrosion than TIG CUA8NI.

Main applications: Shipbuilding (accessories, propulser fans), pumps...

Typical Chemical Composition (%)

	Al	Fe	Mn	Ni+Co	Pb	Si	Zn	O/T	Cu
Min	8.5	3.0	0.60	4.0					
Max	9.5	5.0	3.5	5.5	0.02	0.10	0.10	0.50	Rem.
Type	8.8	3.4	1.5	4.5	0.002	0.04	0.005	<0.50	Rem.

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)
Min	-	-	-
Max			
Type	400	700	15

Welding Current & Instructions

Welding mode	Shielding Gas
GTAW = -	ISO 14175: I1 (100% Ar) / I2 (100% He) / I3 (Ar+ 5-30%He) 5-10 L/min

Preheating of massive parts between 200°C (>6mm) up to 500°C (>15mm).

FT En-TU10-170220

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group.

Fumes: Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr