



TIG CUS8

Old reference: TIG CuSn8

Classification

ISO 24373 : S Cu 5210 (CuSn8P)

Description & Applications

Solid rod for GTAW of Copper-Tin bronzes alloys.

Main applications: For surfacing of wearing surfaces and welding of galvanized sheets.

Typical Chemical Composition (%)

	Fe	Ni	P	Pb	Sn	Zn	O/T	Cu
Min			0.01		7.5			
Max	0.1	0.2	0.4	0.02	8.5	0.1	0.2	Rem.
Type	0.001	0.001	0.08	0.002	8.0	0.008	<0.2	Rem.

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)
Min	-	-	-
Max			
Type		260	20

Welding Current & Instructions

Welding mode	Shielding Gas
GTAW = -	ISO 14175: I1 (100% Ar) / I2 (100% He) / I3 (Ar+ 5-30%He) 5-10 L/min

Preheating of massive parts between 200°C (>6mm) up to 500°C (>15mm).

FT En-TU03-170217

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group.

Fumes: Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr