



TIG HB60

Old reference: TIG R600B

Classification

EN 14700 : S Fe8

Description & Applications

Copper coated solid rod for GTAW. Used for hardfacing parts subject to high impact and medium abrasion. A kind of a universal hardfacing wire used in quarries, mines, steel works, cement works, crushing plants, the wood industry, in the car industry and others.

Main applications: Hardfacing of block presses, crusher jaws, wheel rims, rollers, caterpillar tracks, ploughshares, running surfaces, cutting edges etc

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	P	S	W	V	Ti	Nb	Fe
Min	0.2			5										
Max	2		3	20		5				2	2		10	Rem.
Type	0.45	3.0	0.45	9.5	0.20	0.10	0.20	0.02	0.01	0.02	0.06	0.01	0.01	Rem.

All Weld Metal Mechanical Properties

Hardness (As welded)
~60 HRC

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175 : I1 (Ar) 6-12 l/min

Tool steels have to be preheated to 300-400°C, depending on the thickness and composition.

FT En-TR14-200408

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr