



TIG NI276

Old reference: TIG Ni276

Classification

AWS A5.14 : ERNiCrMo-4

ISO 18274 : S Ni 6276 (NiMo16Cr15Fe6W4)

Description & Applications

Solid rod for GTAW of alloys with similar composition like alloys C-276 and others and other highly corrosion resistant Ni-Cr-Mo alloys as well as special stainless steels. Very resistant in sulphurous acid environment, highly concentrated with chlorides and also in the presence of oxidizing solutions (FeCl, CuCl).

Main applications: Chemical industry, piping systems, equipment of de-pollution

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Mo	Cu	P	S	Fe	W	Co	V	Ni	O/T
Min				14.5	15.0				4.0	3.0			50.0	
Max	0.02	0.08	1.0	16.5	17.0	0.50	0.04	0.03	7.0	4.5	2.5	0.35		0.50
Type	0.010	0.05	0.45	16.0	16.0	0.01	0.007	0.003	6.0	3.5	0.03	0.04	>50.0	<0.50

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	-	-	-	-
Max				
Type	480	780	35	+20°C 100

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175: I1 (Ar) : 6-12 l/min Back shielding : I1 (Ar) : 3-6 l/min

FT En-TI09-200825

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr