



TIG NI60

Old reference: TIG Ni60

Classification

AWS A5.14 : ERNiCu-7

ISO 18274 : S Ni 4060 (NiCu30Mn3Ti)

Description & Applications

Solid rod for GTAW of "Monel" alloy (alloy 400) for components for chemical and petrochemical installations, for sea water and off shore applications. Excellent resistance against corrosion. Recommended for steels/ Copper-Nickel or steels/Copper/Copper Nickel alloys assemblies.

Main applications: Chemical industries, ship building, desalination equipments...

Base materials

UNS	Alloy	DIN	Material N°
C70600	CuNi90/10	CuNi10Fe1Mn	2.0872
C71500	CuNi70/30	CuNi30Mn1Fe	2.0882
N04400	400	NiCu30Fe	2.4360
N05500	K-500	NiCu30Al	2.4375

Typical Chemical Composition (%)

	C	Si	Mn	Cu	P	S	Fe	Nb	Al	Ti	Ni
Min				28.0						1.5	62.0
Max	0.15	1.2	4.0	32.0	0.020	0.015	2.5	0.3	1.2	3.0	69.0
Type	0.03	0.40	3.5	29.0	0.010	0.005	0.60	0.02	0.09	2.2	65.0

All Weld Metal Mechanical Properties

	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	KV (J)
Min	-	-	-	-
Max				
Type	320	510	38	+20°C 180

Welding Current & Instructions

Welding mode	Shielding Gas
TIG = -	ISO 14175: I1 (Ar) : 6-12 l/min Back shielding : I1 (Ar) : 3-6 l/min

FT En-TI03-200831

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr