



FLUX UP LA02

*Agglomerated Aluminate-Basic
Welding Flux*

Classification

ISO 14174 : S A AB 1 67 AC H5

Description & Applications

Aluminate-Basic agglomerated Flux with high current-carrying capacity for submerged arc welding (SAW-process) of unalloyed, low-alloy structural steels, fine-grained steels and pipe steel qualities especially by tandem arc configuration. Metallurgical characteristic of this flux is medium Mn - Si pick up. Flux UP LA02 is formulated to achieve very low diffusible hydrogen levels, easy slag detachability, even in narrow groove welds.

Could be used on D.C and A.C welding, using Single, Tandem, Twin or multi wire welding.

Wires recommended for

ISO 14171-A	AWS A5.17
S1	EL12
S2	EM12
S2Si	EM12K
S3Si	EH12K
S2Mo	EA2
S2Ni2	ENi2

Typical Chemical Composition (%)

SiO ₂ + TiO ₂	Al ₂ O ₃ + MnO	CaO + MgO	CaF ₂	Basicity according To Boniszewski
20	30	35	10	~1.9

Flux Properties

Density (kg / dm ³)	Grain size ISO 14174	Current carrying capacity
1.1	2 - 20 ; Tyler 8x48	Up to 1500A (AC or DC) using one wire

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.



FLUX UP LA02

Agglomerated Aluminate-Basic
Welding Flux

All Weld Metal Typical Chemical analysis (%)

Wire	C	Si	Mn	Ni	Mo
S1	0.05-0.08	0.2-0.4	0.9-1.3		
S2	0.05-0.08	0.2-0.4	1.4-1.8		
S2Si	0.05-0.08	0.2-0.5	1.4-1.8		
S3Si	0.05-0.08	0.2-0.5	1.6-2.0		
S2Mo	0.04-0.08	0.2-0.4	1.3-1.7		0.5
S2Ni2	0.05-0.08	0.2-0.4	1.1-1.5	2.0	

All Weld Metal Typical Mechanical Properties

Wire	R _{p0,2} (MPa)	R _m (MPa)	A (%)	0°C	-20°C	KV (J)	-40°C	-51°C
S1	>400	>510	>24	>80	>47			
S2	AW	>420	>500	>22	>100	>70	>50	
	S*	>400	>490	>22	>110	>80	>60	
S2Si	AW	>430	>520	>22	>100	>70	>50	
	S*	>400	>490	>22	>110	>80	>60	
S3Si	AW	>470	>560	>22	>120	>90	>70	
	S*	>400	>490	>22	>130	>100	>80	
S2Mo	AW	>500	>570	>20	>100	>80	>47	
	S**	>470	>570	>22	>110	>70	>47	
S2Ni2	AW	>540	>520	>22	>150	>120	>70	>47
	S**	>470	>550	>24	>150	>120	>100	>60

* After PWHT at 580°C/1h

** After PWHT at 620°C/15h

Storage Recycling and Drying

It is recommended to store and use the flux up to 1 year after delivery in dry storage rooms. Nevertheless, the flux can be used even if stored for more than one year, just requires the user to make a weldability test to check if all is well.

Drying conditions specific to the flux: 200 ± 50°C. Supplied in moisture proof packaging.