



UP S3

Désignation normalisée

AWS A5.17 : EH10K
AWS A5.23 : EH10K

ISO 14171-A : S3

Propriétés et Applications

Fil plein cuivré pour le soudage à l'arc submergé (sous flux) des aciers non allié (C-Mn).

Principales applications : Construction automobile, ferroviaire, navale. Construction et maintenance d'équipements de travaux publics. Mines, Carrières, matériel agricole...

Nuances soudables:

Aciers de construction à usage général:

EN	ASTM
S275 – S355	A106 grade A, B, C
P275 – P355	A131 grade A, B, D
L210 – L360	A139
	A210 grade A1, C

Typical Chemical Composition (%)

	C	Si	Mn	Cr	Ni	Mo	Cu	Al	P	S	Fe
Min	0.07	0.05	1.30								
Max	0.15	0.15	1.70	0.15	0.15	0.15	0.30	0.030	0.025	0.025	Base
Type	0.12	0.08	1.5	0.04	0.05	0.01	0.10	0.005	0.010	0.008	Base

Paramètres et Conditions d'emploi

	Ø (mm)	Paramètres de Soudage				Flux
		Intensité (A)	Tension (V)	Stick out (mm)	Vitesse (cm/min)	
SAW AC / =+	2.4	360 - 450	25 - 30	18	40 - 60	UP LA04
	3.2	400 - 500	28 - 32	20	40 - 60	UP LA05
	4.0	500 - 600	30 - 35	22	50 - 60	UP BF10

FT-Fr-SA02-171124

Liability: This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company FSH Welding Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for FSH Welding Group. **Fumes:** Consult information on MSDS, available upon request.

www.fsh-welding.com - info@fsh-welding.fr