



## MIG NI65

### Classification

AWS A5.14 : ERNiFeCr-1

ISO 18274 : S Ni 8065 (NiFe30Cr21Mo3)

### Description & Applications

Solid wire for GMAW of Nickel-Iron-Chromium-Molybdenum alloys which has a good resistance to oxidizing and reducing agents like sulphuric and phosphoric acid as well as sea water.

**Main applications:** Chemical and petrochemical industry, ship building, installations for sea water desalination.

#### Base materials:

UNS	Alloy	DIN	Material N°
N08825	Alloy 825	NiCr21Mo	2.4858

### Typical Chemical Composition ( % )

	C	Si	Mn	Cr	Mo	Cu	P	S	Fe	Al	Ti	Ni
Min				19.5	2.5	1.5			22.0		0.6	38.0
Max	0.05	0.50	1.0	23.5	3.5	3.0	0.03	0.03		0.20	1.2	46.0
Type	0.02	0.20	0.60	20.5	3.2	1.8	0.01	0.01	Rem.	0.15	0.90	41.0

### All Weld Metal Mechanical Properties

	R <sub>p0.2</sub> ( MPa )	R <sub>m</sub> ( MPa )	A <sub>5</sub> ( % )	KV ( J )
Min	-	-	-	-
Max	-	-	-	-
Type	350	600	16	-

### Welding Current & Instructions

Welding mode	Wire Ø (mm)	Welding parameters		Shielding Gas
		Current ( A )	Voltage ( V )	
GMAW = +	0.8	70 - 180	18 - 26	ISO 14175: I1 (100% Ar) I3 (Ar+10-30%He) Z (Ar+He+H+CO <sub>2</sub> ) 15-20 l/min
	1.0	80 - 220	18 - 28	
	1.2	150 - 320	22 - 32	
	1.6	220 - 380	24 - 34	

FT En-MI15-260427

**Liability:** This document is intended to assist the user in choosing the product. It is up to the user to verify that the chosen product is suitable for applications for which it is intended. The company Selectarc Group reserves the right to alter specifications without prior notice of its products. The descriptions, illustrations and specifications are for reference only and cannot be held liable for Selectarc Group. **Fumes:** Consult information on MSDS, available upon request.

[www.selectarc.com](http://www.selectarc.com) - [info@selectarc.fr](mailto:info@selectarc.fr)